



Nombre Name Nom	Composición Composition Composition	Peso Weight Poids	Martindale UNE-EN ISO 12947-2	Pilling UNE-EN ISO 12945-2	Costuras Seam slippage Glissement des fils de couture UNE-EN ISO 13936-2		Estabilidad dimensional al lavado (30° C) Shrinkage to washing Retrait au lavage		Aplicaciones Application Application	Instrucciones de lavado Care instructions Entretien
					Urd. Warp Chaine	Trama Weft Trame	Urd. Warp Chaine	Trama Weft Trame		
BASILEA	100% PES FR	360 g/m²	30.000	3-4	< 4 mm	< 3,5 mm	≤ 2%	≤ 2%		
BIASCA	100% PES FR	360 g/m²	20.000	4-5	< 4,5 mm	< 4,5 mm	≤ 1,5%	≤ 3%		
CUERA	100% PES FR	310 g/m²	25.000	4-5	< 3 mm	< 4 mm	≤ 1%	≤ 2%		
LAUSANA	100% PES FR	440 g/m²	30.000	4-5	< 3,5 mm	< 3,5 mm	≤ 1,5%	≤ 3%		
LUCERNA	100% PES FR	335 g/m²	20.000	4-5	< 5 mm	< 5 mm	≤ 1,5%	≤ 2,5%		
LYSS	100% PES FR	340 g/m²	50.000	4-5	< 4 mm	< 5 mm	≤ 2%	≤ 3%		

MADE IN SPAIN FABRICS



COLLECTION
HELVETIA

DIRECCIÓN Y RAPPORT DEL TEJIDO / DESIGN DIRECTION AND PAPPORT

BASILEA
RAPPORT: 0,4 cm
0,5 cm

BIASCA
RAPPORT: cont
10 cm

CUERA
RAPPORT: 3 cm
cont

LAUSANA
RAPPORT: cont
cont

LUCERNA
RAPPORT: 6 cm
8 cm

LYSS
RAPPORT: cont
cont





Lucerna 15

Basilea 15

Lausana 15

Cuera 15

Biasca 15

Lyss 15

Lucerna 07

Basilea 07

Lausana 07

Cuera 07

Biasca 07

Lyss 07



Lucerna 10

Basilea 10

Lausana 10

Cuera 10

Biasca 10

Lyss 10

Lucerna 19

Basilea 09

Lausana 19

Cuera 19

Basilea 19

Lyss 19



Lucerna 22

Basilea 22

Lausana 22

Cuera 22

Biasca 22

Lyss 22

Lucerna 99

Basilea 99

Lausana 99

Cuera 99

Biasca 99

Lyss 99