





KENDALL LISO 3934 Optik



KENDALL PANAMA
8013 Grafito



COCOA 90




SANFORD 90



TAMARAC 90



SANFORD 90 REV




KENDALL LISO 3732 Negro




TAMARAC 04



KENDALL LISO 3934 Optik



SANFORD 04



KENDALL LISO 3729 Mineral



COCOA 04



SANFORD 04 REV




KENDALL PANAMA
8001 Coco



DINEDIN 01



SANFORD 01



KENDALL PANAMA
8008 Lino




OCALA 01



KENDALL LISO 3934 Optik




SANFORD 01 REV



KENDALL LISO 1227 Marmol



DINEDIN 22



SANFORD 22 REV



OCALA 22



KENDALL LISO OPTIK 3934



SANFORD 22



KENDALL PANAMA
3739 Blanco



KENDALL LISO
3718 Brasserie






WILMA 07



KENDALL LISO 3934 Optik



SANFORD 07



KENDALL PANAMA
3739 Blanco



LANTANA 07 REV



SANFORD 07 REV



KENDALL LISO 3722 Azul



LANTANA 07



WILMA 10




KENDALL LISO 3934 Optik



SANFORD 10




KENDALL PANAMA
3739 Blanco



LANTANA 10 REV



KENDALL LISO
3708 Mostaza



SANFORD 10 REV



LANTANA 10





TAMARAC

RAPPORT: 13,5 cm
10,5 cm



DINEDIN

RAPPORT: 20,5 cm
22,5 cm




WILMA

RAPPORT: 20,5 cm
20 cm



KENDALL PANAMA

RAPPORT: cont.
cont.



KENDALL LISO

RAPPORT: cont.
cont.




COCOA

RAPPORT: 20,5 cm
17,5 cm



OCALA

RAPPORT: 13,5 cm
12 cm



LANTANA

RAPPORT: 13,5 cm
23 cm



SANFORD

RAPPORT: cont.
cont.

	Composición Composition Composition	Ancho Width Laize	Peso Weight Poids	Martindale UNE-EN ISO 12947-2	Pilling UNE-EN ISO 12945-2	Solidez a la luz Fastness to light Résistance à la lumière ISO 105-B02	Costuras Seam slippage Glissement des fils de couture UNE-EN ISO 13936-2		Estabilidad dimensional al lavado (30° C) Shrinkage to washing Retrait au lavage		Aplicaciones Application Application	Condiciones de lavado Clean recommendation Recommandation d'entretien
							Urdimbre Warp Chaîne	Trama Weft Trame	Urdimbre Warp Chaîne	Trama Weft Trame		
COCOA	100% Solution Dyed Acrilic	160 cm	375 g/m ²	20000	4	7-8	< 4 mm	< 4 mm	≤ 2,5%	≤ 1%		
DINEDIN	100% Solution Dyed Acrilic	160 cm	375 g/m ²	20000	4	7-8	< 5 mm	< 4 mm	≤ 2%	≤ 1,5%		
KENDALL LISO	100% Solution Dyed Acrilic	160 cm	250 g/m ²	30000	4-5	7-8	< 5 mm	< 3 mm	≤ 1,5%	≤ 0,5%		
KENDALL PANAMA	100% Solution Dyed Acrilic	160 cm	290 g/m ²	25000	4	7-8	< 5 mm	< 4 mm	≤ 1,5%	≤ 1%		
LANTANA	100% Solution Dyed Acrilic	160 cm	380 g/m ²	20000	4	7-8	< 4 mm	< 4 mm	≤ 2,5%	≤ 1,5%		
OCALA	100% Solution Dyed Acrilic	160 cm	375 g/m ²	20000	4	7-8	< 4 mm	< 4 mm	≤ 2,5%	≤ 1%		
SANFORD	100% Solution Dyed Acrilic	160 cm	450 g/m ²	30000	4	7-8	< 5 mm	< 5 mm	≤ 3%	≤ 2,5%		
TAMARAC	100% Solution Dyed Acrilic	160 cm	425 g/m ²	20000	4	7-8	< 5 mm	< 5 mm	≤ 1,5%	≤ 1%		
WILMA	100% Solution Dyed Acrilic	160 cm	350 g/m ²	20000	4	7-8	< 5 mm	< 5 mm	≤ 2,5%	≤ 1%		